



DEV INDUSTRIAL COATINGS

(Manufacturers of Hi-Tech Industrial Paints)

(AN ISO 9001:2008 CERTIFIED COMPANY)

<u>"NAGARJUNA" POLYCOAT</u> <u>2K-POLYURETHANE PRIMER</u>	
PRODUCTION DESCRIPTION	"Nagarjuna" Polycoat Primer is a two component (2K) polyurethane primer having anti-corrosive rust inhibitive pigments
RECOMMENDED USE	"Nagarjuna" Polycoat Primer must be used where a finished coat of polycot PI/PII paint is to be applied. It has excellent adhesion to a wide range of substrates like metal, wood FRP, concrete
PROPERTIES	
Finish	Matt
Shade	White/Grey
Standard coverage	8-9 sq.mts/ltr
Specific Coverage	1.2-1.4 kg/ltr
Flash point	31 deg. C
Touch Dry	Less than 30minutes
Surface Dry	1-2 hours
Hard Dry	12 hours
Scratch Hardness(min)	1000 grams
DFT	25 microns
APPLICATION SYSTEM	
Mixing Ratio	Part A: Part B 3:1 by volume
Method of application	Airless spray/Air spray/Brush
Compatible Thinner	"Nagarjuna"PU Part-C
Compatible Finish Paint	"Nagarjuna"Polycoat PI/PII
Pot Life (min)	6hours
Recoatable Interval	12hours
Packing	20 Ltrs
Storage Life	As long as the material remains unmixed and the containers are kept firmly sealed, the contents can be stored upto 6 months without deterioration
Specifications, and data given above represent test results obtained under controlled Conditions. These may vary under actual circumstance	

PRODUCT CODE: DIC/901



Plot No. 8A, Rasoolpura, Secunderabad - 500 003. A.P. India.

Tel : 040-27901196, Telefax : 040-27906871, E-mail : jnanadev@devindustrialcoatings.com