



DEV INDUSTRIAL COATINGS

(Manufacturers of Hi-Tech Industrial Paints)

(AN ISO 9001:2008 CERTIFIED COMPANY)

<u>"NAGARJUNA" POLYCOAT P 1</u> <u>2K- POLYURETHANE PAINT</u>	
PRODUCT DESCRIPTION RECOMMENDED USE	"Nagarjuna Polycoat P1 is a two component aliphatic polyurethane paint with very good colour retention and gloss: Even under UV rays the coating has very good resistance to atmospheric weathering conditions. Long lasting finish coat in chemical and fertilizer plants, storage tanks earth moving equipments and structures also wherever high abrasion resistant and exterior durability is required
PROPERTIES Finish Shade Standard coverage Specific gravity Flash point Touch Dry Surface Dry Hard Dry Scratch Hardness(min) DFT	High Gloss/semi-gloss /matt Any shade/clear ,as per R.A.L, IS:5 10-12 sq.mts/ltrs 1.0-1.2 kg/ltr 31C Less than 30 minutes 1- 2 hours 12 hours 2000 grams 25 microns
APPLICATION SYSTEM Mixing Ratio Method of application Compatible Thinner Compatible Primer Pot Life(min) Recoatable interval Packing Storage Life	Part A: Part B 3:1 by volume Airless Spary/Airspray/Brush "Nagarjuna" PU Part-C "Nagarjuna" 2K Polycoat Primer 6 hours 6 hours 20Lts As Long as the material remains unmixed and the containers are kept firmly sealed, the contents can be stored upto 6 months without deterioration
Specification, and data given above represent test results obtained under controlled Conditions. These may vary under actual circumstance	

PRODUCT CODE: DIC/101

